

TECHNICAL DATA SHEET

Scheda Tecnica

Mod. PG 7.06-01 rev.3 del 18/03/10

Product GLAM SILVER 1/S	Weight 115 g/m²
--	---

Characteristic	Internal Method	Standard Reference	Unit of Measure	Side or Direction	Specific Values	Tolerance 2σ
Substance	PO 301	ISO 536	g/m ²	-	115	± 5%
Thickness	PO 303	ISO 534	µm	-	135	± 5%
Absolute Humidity	PO 302	ISO 287	%	-	6,0	± 1,0
L&W Stiffness (15°/ 10 mm)	PO 323	ISO 2493	mN	MD	160	>
L&W Stiffness (15°/ 10 mm)	PO 323	ISO 2493	mN	CD	80	>
Roughness Bendtsen	PO 309	ISO 8791-2	ml/min	-	250	± 100

The technical data sheet shall be deemed accepted if not challenged within one month of receipt.

Emission Date	01/12/2021
TDS n°	02MGM
Period of Validity	Until next review
R&S Manager	Renato Burba

Our internal methods are based upon the indicated official methods, but could differ in some details. The above data have been agreed in good faith and tested to the best of our knowledge, but we cannot guarantee the results of further reprocessing that are beyond our control.

We recommend that the Clients, in all cases, evaluate if the characteristics of our paper fit their actual needs and the requirements of the final products.

TECHNICAL DATA SHEET

Scheda Tecnica

Mod. PG 7.06-01 rev.3 del 18/03/10

Product GLAM SILVER	Weight 120 g/m²
--------------------------------------	---

Characteristic	Internal Method	Standard Reference	Unit of Measure	Side or Direction	Specific Values	Tolerance 2σ
Substance	PO 301	ISO 536	g/m ²	-	120	± 5%
Thickness	PO 303	ISO 534	µm	-	140	± 5%
Absolute Humidity	PO 302	ISO 287	%	-	6,0	± 1,0
L&W Stiffness (15°/ 10 mm)	PO 323	ISO 2493	mN	MD	180	>
L&W Stiffness (15°/ 10 mm)	PO 323	ISO 2493	mN	CD	90	>
Roughness Bendtsen	PO 309	ISO 8791-2	ml/min	-	250	± 100

The technical data sheet shall be deemed accepted if not challenged within one month of receipt.

Emission Date	01/12/2021
TDS n°	02AGM
Period of Validity	Until next review
R&S Manager	Renato Burba

Our internal methods are based upon the indicated official methods, but could differ in some details. The above data have been agreed in good faith and tested to the best of our knowledge, but we cannot guarantee the results of further reprocessing that are beyond our control.

We recommend that the Clients, in all cases, evaluate if the characteristics of our paper fit their actual needs and the requirements of the final products.

TECHNICAL DATA SHEET

Scheda Tecnica

Mod. PG 7.06-01 rev.3 del 18/03/10

Product GLAM SILVER	Weight 290 g/m²
--------------------------------------	---

Characteristic	Internal Method	Standard Reference	Unit of Measure	Side or Direction	Specific Values	Tolerance 2σ
Substance	PO 301	ISO 536	g/m ²	-	290	± 5%
Thickness	PO 303	ISO 534	µm	-	340	± 5%
Absolute Humidity	PO 302	ISO 287	%	-	6,0	± 1,0
L&W Stiffness (15°/ 50 mm)	PO 325	ISO 2493	mN	MD	160	>
L&W Stiffness (15°/ 50 mm)	PO 325	ISO 2493	mN	CD	80	>
Roughness Bendtsen	PO 309	ISO 8791-2	ml/min	-	250	± 100

The technical data sheet shall be deemed accepted if not challenged within one month of receipt.

Emission Date	01/12/2021
TDS n°	02BGM
Period of Validity	Until next review
R&S Manager	Renato Burba

Our internal methods are based upon the indicated official methods, but could differ in some details. The above data have been agreed in good faith and tested to the best of our knowledge, but we cannot guarantee the results of further reprocessing that are beyond our control.

We recommend that the Clients, in all cases, evaluate if the characteristics of our paper fit their actual needs and the requirements of the final products.